

GODRY MAXCOAT 2X

Application Procedure



01



Clean the surface thoroughly and repair the damaged surface using repair mortar.

02



Shake the liquid component (Part A) well and pour it into a clean plastic or metal bucket/drum.

03



Add the powder component (Part B) gradually to the liquid avoiding any lump formation while constantly mixing with a stirrer or a paddle.

04



Mix for 2-3 minutes to a homogeneous and uniform consistency.

05



For best results, moisten the surface with clean water prior to application.

06




Apply the 1st coat of mixed material using a short, stiff bristle brush over the surface.

07



Once the 1st coat reaches touch dry state, Apply the 2nd coat to achieve a combined thickness of 1 to 2mm.

08



The applied area should be protected from direct sunlight and should be damp cured by placing wet hessian or similar system.

For more information about GODRY, please visit www.godry.co.in.

Manufactured by:



VNC Electrodes, S. Vellalapatti, Karur - 639004
☎ 1800 425 8862 ✉ contactusevncgroup.com
🌐 www.vncgroup.com

